

## TECHNICAL DATA SHEET

Art.No. 13055

### WILDBRETT Parquet Adhesive hartelastisch weichmacherfrei 1K-SMP



- Universal adhesive
- Elastic hard adhesive ridge
- Free from migratory components
- Free from water and solvents

### PRODUCT PROPERTIES

This high quality and single-component adhesive is free from water and solvents. It is based on MS technology, does not contain any migratory components and does not cause damaging interaction with WILDBRETT parquet lacquers.

### APPLICATION

It is suitable for indoor use only and is applied to bond strip parquet according to DIN EN 13226, on edge according to DIN EN 14761, mosaic parquet according to DIN EN 13488 and solid wood planks as well as for multilayer parquet of 2 and 3 layers (also single strips). The adhesive is suitable for underfloor heating systems.

### PRODUCT DATA

Delivery form: Plastic bucket of 16 kg, 33 plastic buckets / 528 kg per pallet

Storage: Store the product in a frost-free, cool and dry place on a wooden grid. The product is durable in the original sealed packaging for approx. 12 months.

### TECHNICAL DATA

Consumption: approx. 1,0 to 1,8 kg/m<sup>2</sup> depending on the kind of parquet, substrate and trowel toothing

Specific weight: 1,6 g / cm<sup>3</sup>

Processing time: approx. 30 to 35 minutes

Final strength: after approx. 48 hours

Ideal processing temperature: +16 °C to +25 °C

All data are average values, which were determined under laboratory conditions. Due to the use of natural raw materials, the given data may slightly differ in a single lot without affecting the product suitability.

### PROCESSING

Underground:

The substrate must be dry, frost-free, firm, load bearing, dimensionally stable and free from dust, dirt, oil, fat, separating agents and loose parts and must correspond to the current technical national and European standards as well as to the "generally acknowledged rules of the trade".

Recommended tool:  
B3, PK5, PK8-B17

Pre-treatment:

Pre-treat the substrate using WILDBRETT products. Appropriate priming: PU Express.

Processing:

Apply the adhesive evenly to the substrate using an appropriate notched trowel with big toothing. The laying period is approximately 30 to 35 minutes. Lay the parquet onto the adhesive bed moving it slightly into place and then pressing it down firmly in order to spread the adhesive across the entire reverse side of the parquet. You can walk over the parquet after approximately 24 hours. At low temperatures, the hardening process can be delayed.

Polish the parquet flooring for the first time after at least 48 hours. The wood humidity at the time of laying must comply with the valid ÖNORM standards. Observe the parquet manufacturer's instructions. The adhesive joint reduces shear forces and inhibits the transmission of damaging forces to the substrate. Remove adhesive stains from the parquet within a period of approximately 1 to 2 hours after laying rubbing them slightly. After setting, the adhesive can only be removed mechanically.

### IMPORTANT NOTES

Adhere to the norms, guidelines and datasheets regarding subsurface. Do not process at temperatures below +15°C. High levels of humidity and low temperatures delay and high temperatures accelerate the setting and hardening. Do not add external materials.

### HEALTH AND SAFETY

Health and safety: Product-specific information regarding the composition, handling, cleaning, relevant measures and disposal can be found in the safety data sheet.

This data sheet is based on comprehensive experiences, intends to inform to the best knowledge, is not legally binding and does not constitute a contractual legal relationship or a side obligation from the purchase agreement. We guarantee for the quality of our products under our terms and conditions of sale and purchase. In to reduce the risk of error, limiting information is also stated. Naturally, not all possible current and future application cases and peculiarities can be included in full. Information, which can be considered to be known amongst specialists, has not been included. The user can not be released from a query in the event of confusion, testing on site under his own responsibility as well as specialist processing. On issuing a new version of the print shall become invalid.

Version: November 2015

